



# EPL-9™

## SELF-LEVELING POLYUREA ELASTOMER

PRELIMINARY  
Revised 07.05.11

### DESCRIPTION

EPL-9™ is a slow set, self-leveling elastomer.

### FEATURES

- Gel time of approximately 9 minutes (77°F (25°C)).
- May be hand mixed, static mixer processed, or sprayed.
- 100% solids. Zero VOCs.
- Meets FDA/USDA requirements for incidental food contact.

### RECOMMENDED USES

- Self-leveling base coat
- Spot repair of pre-existing coatings
- Deck repairs
- Crack repairs
- Hard to reach places not accessible to spray equipment
- Control joint filler
- Warehouse floor repairs

### COLORS

EPL-9™ is available in SPI standard Black. Custom colors will be quoted upon request. It should be noted that EPL-9™ is an aromatic polyurea; therefore, as with all aromatics, color change and superficial oxidation will occur.

Aliphatic urethane, polyurea, and other suitable topcoats can be used when long term color stability and increased longevity in full sun exposure are of critical importance.

### WET PROPERTIES

<b>Solids by Volume</b>	100%
<b>Solids by Weight</b>	100%
<b>Volatile Organic Compounds</b>	0 lbs/gal (0g/l)
<b>Theoretical Coverage DFT</b>	100 sq. ft. @ 16 mils/gal
<b>Weight per Gallon</b>	8.8 lbs. (3.99 kg) approx.
<b>Mix Ratio</b>	1 "A": 1 "B"
<b>Shelf Life Unopened Containers @ 60-90°F (15-32°C)</b>	Six months

Minimum material/container temperature for EPL-9 application is 70°F (21 °C).

### DRY PROPERTIES\* Static Mixer

<b>Tensile Strength</b> ASTM D 412	>1700 psi ( 11.81mpa)
<b>Elongation</b>	>330%
<b>Hardness (Shore A)</b>	90 (0) sec
<b>Hardness (Shore D)</b>	40 (0) sec
<b>Stress Modulus 100%</b>	>800
<b>Stress Modulus 300%</b>	>1580
<b>Service Temperature</b>	-40°F - +200°F (-40°C- +93°C)

*\*All cured film properties are approximate since processing parameters, ad-mixture types, and quantities will change physical properties of cured elastomer. All samples for above tests were force cured or aged for more than three weeks. It is recommended that the user perform their own independent testing.*

### CURING SCHEDULE

<b>Pot Life @ 77°F (25°C)</b>	±9 min.
<b>Tack Free @ 77°F (25°C)</b>	1 hour approx
<b>Final Cure*</b>	3-4 days

\*Elevated temps will speed up the curing process.

### INSTALLATION

- Mix @ 1:1 ratio for two minutes.
- Some applications may require use of a primer prior to application of the sealant depending on substrate.
- **Due to very short pot life, all materials must be used immediately after mixing.**

Follow the instructions attached to "A" and "B" containers.



SPI - The Single Source Solution Since 1974  
Serving the Plural-Component Industry

Product & Equipment Technical Assistance  
24 hours / 7 days a week (800) 627-0773

**Note: Currently, this product is manufactured exclusively by our Lakewood, Washington facility. Therefore, please allow additional transit time as well as additional transportation charges to certain geographic areas.**

## LIMITATIONS

- EPL-9™ is for professional application only.
- EPL-9™ must be stored at temperatures between 60° F to 90° F (15 °C to 30 °C). Minimum material/container temperature for spray application is 70°F(21 °C).
- Liquid temperature in drums during application 70°F (21°C) – 100°F (38°C).
- Apply EPL-9™ when surface and air temperatures are above 40°F (5°C) and rising, and 7°F (-13°C) above dew point.
- Avoid moisture contamination in containers. Containers should not be resealed if contamination is suspected, carbon dioxide (CO<sub>2</sub>) created pressure can develop. Do not attempt to use contaminated material.
- Read and observe all precautions, instructions and limitations that are included with all containers of EPL-9™.
- EPL-9™ is a “slow set” (minutes) polyurea and may behave differently in the presence of moisture than the fast-set (seconds) polyurea.
- Undried air exposed to liquid components will reduce physical properties of the cured coating.

**Note:** The material supplied is two components (“A” and “B”) used to formulate EPL-9™. The mixture and application of the two components determine the quality and characteristics of the finished polymer.

## GENERAL SAFETY, TOXICITY & HEALTH DATA

Material Safety Data Sheets are available for this coating material. Any individual who may come in contact with these products should read and understand the M.S.D.S. **CHEMTREC EMERGENCY NUMBER 1-800-424-9300**

**WARNING:** Contact with skin or inhalation of vapors may cause an allergic reaction. Avoid eye contact of the liquid or spray mist.

**CLEAN UP:** Use DPM, NMP, Polyclean.

**EYE PROTECTION:** Safety glasses, goggles, or a face shield are recommended.

**SKIN PROTECTION:** Chemical resistant gloves are recommended. Cover as much of the exposed skin area as possible with appropriate clothing.

**INGESTION:** Do not take internally. It is believed ingestion of polymeric isocyanates would not be fatal to humans, but may cause inflammation of mouth and stomach tissue.

**RESPIRATORY PROTECTION:** Use a respirator approved for isocyanates and organic vapors. If you are not sure or not able to monitor levels, or if you are spraying in an enclosed/indoor area, use MSHA/NIOSH approved supplied air respirator. Consider the application and environmental concentrations in deciding if additional protective measures are necessary.

## WARRANTY & DISCLAIMER

Specialty Products, Inc. has no role in the manufacture of the finished polymer other than to supply its two components. It is vital that the person applying this product understands the product, and is fully trained and certified in the use of plural-component equipment.

Specialty Products, Inc., an Alaska corporation, warrants only that the two components of this product shall conform to the technical specifications published in the product literature.

The quality and fitness of the product are dependent upon the proper mixture and application of the components by the applicator. There are no warranties that extend beyond the description on the face of this instrument.

**SPECIALTY PRODUCTS, INC. MAKES NO WARRANTY OF MERCHANTABILITY OF THE PRODUCT OR OF FITNESS OF THE PRODUCT FOR ANY PARTICULAR PURPOSE.**

Specialty Products, Inc. makes no warranty as to the quality of any product modified, supplemented, tinted, or altered in any way after it leaves the manufacturing plant. Specialty Products, Inc. does not warrant that this product is suitable for use as a liner for potable

water containers. Use of this product in a potable water container could be hazardous to health if it is improperly processed or applied.

The liability of Specialty Products, Inc. for any nonconformity of the product to its technical specifications shall be limited to replacement of the product.

The sole exclusive remedy of buyer, which is to have Specialty Products, Inc. replace any nonconforming product at no cost to buyer, is conditioned upon buyer notifying Specialty Products, Inc. or its distributor in writing of such defect within thirty days of the discovery of such defect.

Specialty Products, Inc. shall not be liable for any direct, incidental, or consequential damages resulting from any breach of warranty.

The data presented herein is not intended for non-professional applicators or those persons who do not purchase or utilize this product in the normal course of their business.

The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer.

The aforementioned data on this product is to be used as a guide and is subject to change without notice.

The information herein is believed to be reliable, but unknown risks may be present. No warranties, expressed or implied, including patent warranties or warranties of merchantability or fitness of use, are made by Specialty Products, Inc. with respect to products or information set forth herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.

Accordingly, the buyer assumes all risks whatsoever as to the use of these materials and buyer's exclusive remedy as to any breach of warranty, negligence, or other claim shall be limited to the purchase price of the materials. Failure to adhere to any recommended procedures shall relieve Specialty Products, Inc. of all liability with respect to the materials and the use thereof.